



A brand of ITW Polymers Adhesives North America

Fasmetal™ 10 HVAC Repair

Description: An aluminum-filled, 1:1 mix epoxy packaged in 6 1/2 oz. tube kit for repairs to copper coils in HVAC equipment.

Intended Use: Seal leaks in pipes and tanks; repair copper coils in compressors; repair holes in aluminum and other metals

Product features:
Fills voids or pores in castings
Bonds, patches, and seals metals
Good stability in Freon Environment
Bonds to aluminum, concrete, and many other metals
Aids in quickly returning equipment back to service
Hardens to a rigid material that can be ground, drilled, or tapped

Limitations: Not recommended for long term exposure to concentrated acids and organic solvents

Typical Physical Properties: *Technical data should be considered representative or typical only and should not be used for specification purposes.*

Cured 7 days @ 75° F

Adhesive Tensile Shear	2,500 psi
Coefficient of Thermal Expansion	29 [(in.) x (in). x °F)] x 10(-6)
Color	Aluminum
Compressive Strength	8,420 psi
Coverage/lb	30 sq.in./6.5 oz. @ 1/4"
Cured Hardness	85D
Cured Shrinkage	0.0008 in./in.
Dielectric Constant	21.4
Dielectric Strength	100 volts/mil
Flexural Strength	6,260 psi
Functional Cure	16 hrs.
Mix Ratio by Volume	1:1
Mix Ratio by Weight	0.9:1
Mixed Viscosity	40,000 cps
Modulus of Elasticity	7.8 psi x 10(5)
Pot Life @ 75F	60 min.
Recoat Time	10-12 hrs.
Solids by Volume	100
Specific Gravity	1.72 gm/cc
Specific Volume	16.1 in.(3)/lb.
Temperature Resistance	Wet: 110°F; Dry: 250 °F
Thermal Conductivity	1.73[cal/(secxcmx°C)]x10(-3)

TESTS CONDUCTED

Compressive Strength ASTM D 695
Cured Hardness Shore D ASTM D 2240
Dielectric Constant ASTM D 150
Modulus of Elasticity ASTM D 638
Cure Shrinkage ASTM D 2566
Adhesive Tensile Shear ASTM D 1002
Dielectric Strength, volts/mil ASTM D 149
Coef. of Thermal Expansion ASTM D 696
Flexural Strength ASTM D 790
Thermal Conductivity ASTM C 177

Surface Preparation:

1. Thoroughly clean the surface with Devcon® Cleaner Blend 300 to remove all oil, grease and dirt.
2. Grit blast surface area with 8-40 mesh grit, or grind with a coarse wheel or abrasive disc pad, to create increased surface area for better adhesion (Caution: An abrasive disc pad can only be used provided white metal is revealed). Desired profile is 3-5mil, including defined edges (do not "feather-edge" epoxy).

Note: For metals exposed to sea water or other salt solution, grit-blast and high-pressure-water-blast the area, then leave overnight to allow any salts in the metal to "sweat" to the surface. Repeat blasting to "sweat out" all soluble salts. Perform chloride contamination test to determine soluble salt content (should be no more than 40ppm).

3. Clean surface again with Devcon® Cleaner Blend 300 to remove all traces of oil, grease, dust or other foreign substances from the grit blasting.

4. Repair surface as soon as possible to eliminate any changes or surface contaminants.

WORKING CONDITIONS: Ideal application temperature is 55°F to 90°F. In cold working conditions, directly heat repair area to 100-110°F prior to applying epoxy and maintain at this temperature during product cure to dry off any moisture,

contamination or solvents, as well as to achieve maximum performance properties.

Mixing Instructions:

---- It is strongly recommended that full units be mixed, as ratios are pre-measured. ----

1. Add hardener to resin.
2. Mix thoroughly with screwdriver or similar tool (continuously scrape material away from sides and bottom of container) until a uniform, streak-free consistency is obtained.

INTERMEDIATE SIZES (1,2,3 lb. units): Place resin and hardener on a flat, disposable surface such as cardboard, plywood or plastic sheet. Use a trowel or wide-blade tool to mix the material as in Step 2 above.

LARGE SIZES: (25 lb., 30 lb., 50 lb. buckets): Use a T-shaped mixing paddle or a propeller-type Jiffy Mixer Model ES on an electric drill. Thoroughly fold putty by vigorously moving paddle/propeller up and down until a homogenous mix of resin and hardener is attained.

Application Instructions:

Spread mixed material on repair area and work firmly into substrate to ensure maximum surface contact. Fasmetal™ 10 HVAC Repair fully cures in 16 hours, at which time it can be machined, drilled, or painted.

FOR BRIDGING LARGE GAPS OR HOLES

Place fiberglass sheet, expanded metal, or mechanical fasteners between repair area and Fasmetal™ 10 HVAC Repair prior to application.

FOR VERTICAL SURFACE APPLICATIONS

Fasmetal™ 10 HVAC Repair can be troweled up to 1/2" thick without sagging. Chemical immersion is possible after 24 hours.

FOR MAXIMUM PHYSICAL PROPERTIES

Cure at room temperature for 2.5 hours, then heat cure for 4 hours @ 200°F.

FOR ± 70°F APPLICATIONS

Applying epoxy at temperatures below 70°F lengthens functional cure and pot life times. Conversely, applying above 70°F shortens functional cure and pot life.

Storage:

Store at room temperature, 70 °F.

Compliances:

None

Chemical Resistance:

Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75°F

1,1,1-Trichloroethane	Fair	Phosphoric 10%	Fair
Ammonium Hydroxide 20%	Poor	Potassium Hydroxide 40%	Fair
Benzene	Very good	Sodium Chloride Brine	Fair
Cutting Oil	Very good	Sodium Hydroxide 10%	Poor
Gasoline (Unleaded)	Very good	Sodium Hypochlorite	Fair
Hydrochloric 10%	Fair	Sulfuric 10%	Fair
Methyl Ethyl Ketone	Poor	Sulfuric 50%	Poor
Methylene Chloride	Poor	Trisodium Phosphate	Fair

Precautions:

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

For technical assistance, please call 1-800-933-8266

FOR INDUSTRIAL USE ONLY

Warranty:

Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer:

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

Order Information:

19770 6.5 oz. tube